## ADENE OMQBG

## Polypropylene Copolymer

A.D. Compound spa

## Message:

ADENE OMQBG is a Polypropylene Copolymer (PP Copolymer) material filled with 40% talc. It is available in Europe or North America. Primary attribute of ADENE OMQBG: Copolymer.

Typical application of ADENE OMQBG: Automotive

General Information			
Filler / Reinforcement	Talc,40% Filler by Weight		
Features	Copolymer		
Uses	Automotive Applications		
Appearance	Black		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.24	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	8.0	g/10 min	ISO 1133
Ash Content	40	%	ISO 3451-1
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	2400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	3.9	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa,			
Unannealed)	50.0	°C	ISO 75-2/A
Vicat Softening Temperature	74.0	°C	ISO 306/B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

