

Resilience™ LS11170E

Rigid Polyvinyl Chloride

PolyOne Corporation

Message:

Resilience™LS11170E is a rigid polyvinyl chloride product. It can be processed by extrusion and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: lighting equipment.

Features include:

flame retardant/rated flame

High stiffness

General Information			
UL YellowCard	E41877-102476704		
Features	Super rigidity		
	Low CLTE		
Uses	Lighting Applications		
	Profile		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.65	g/cm ³	ASTM D792
PVC Cell Classification	0		ASTM D1784
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	81		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	8070	MPa	ASTM D638
Tensile Strength ² (Yield)	54.7	MPa	ASTM D638
Flexural Modulus	7720	MPa	ASTM D790
Flexural Strength	103	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Compression Molded)	32	J/m	ASTM D256A
Drop Impact Resistance			ASTM D4226
23°C ³	9.34	J/cm	ASTM D4226
23°C ⁴	9.34	J/cm	ASTM D4226
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	79.1	°C	ASTM D648
0.45 MPa, annealed	79.9	°C	ASTM D648
1.8 MPa, not annealed	75.8	°C	ASTM D648
1.8 MPa, annealed	77.9	°C	ASTM D648

CLTE - Flow	2.5E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
	V-0		
Flame Rating (1.3 mm, GY)	5VA	UL 94	
Extrusion	Nominal Value	Unit	
Melt Temperature	182 - 193	°C	
NOTE			
1.	Type 1, 5.1 mm/min		
2.	Type 1, 5.1 mm/min		
3.	Procedure A, C.125 Throwing		
4.	Procedure B, C.125 Throwing		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

