# LOXIM 130 01 V0

### Polycarbonate

### **LOXIM Industries Private Limited**

### Message:

LOXIM 130 01 V0 is a Polycarbonate (PC) product filled with 30% glass fiber. It is available in Asia Pacific. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Appearance	Colors Available		
	Opaque		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43 to 1.45	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.10 to 0.30	%	ASTM D1299
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8000	MPa	ASTM D638
Tensile Strength (Break)	110 to 120	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	6500	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	130 to 150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	150	°C	ASTM D648B
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

