

Razamid® A121

Polyamide 66

Razin™ Engineering Plastics

Message:

Razamid A121 is a general purpose injection grade Black color polyamide 66 resin.

General Information			
Features	General Purpose		
Uses	General Purpose		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.16	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.3 to 2.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	80.0	MPa	ASTM D638
Tensile Elongation (Break)	35	%	ASTM D638
Flexural Modulus	2900	MPa	ASTM D790
Flexural Strength	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	5.00	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	210	°C	
1.8 MPa, Unannealed	80.0	°C	
Vicat Softening Temperature	230	°C	ASTM D1525
Peak Melting Temperature	260	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+13	ohms · cm	IEC 60093
Dielectric Strength	13	kV/mm	ASTM D149
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 110	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	270 to 280	°C	
Middle Temperature	270 to 300	°C	
Front Temperature	270 to 300	°C	
Processing (Melt) Temp	275 to 305	°C	
Mold Temperature	15.0 to 95.0	°C	
Injection Pressure	55.0 to 140	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

