

PTS PPE-LXS314-30

Polyphenylene Ether + PS

Polymer Technology and Services, LLC

Message:

PTS PPE-LXS314-30 is a Polyphenylene Ether + PS (PPE+PS) product filled with 30% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Typical application: Industrial Applications. Primary characteristic: impact resistant.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	High Impact Resistance		
Uses	Industrial Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.35	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/5.0 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	110	MPa	ASTM D638
Tensile Elongation ³ (Break)	6.0	%	ASTM D638
Flexural Modulus ⁴	5500	MPa	ASTM D790
Flexural Strength ⁵	160	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area)	14.0	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	135	°C	ASTM D648
NOTE			
1.	solid		
2.	Type I		
3.	Type I		
4.	2.6 mm/min		
5.	2.6 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

