

CLARIX® 110901-01 Clear

Ionomer

A. Schulman Inc.

Message:

Ionomer Sodium

General Information	
Features	Sodium Ionomer
Appearance	Clear/Transparent
Processing Method	Blown Film
	Cast Film
	Coextruded Film

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.940	g/cm ³	ASTM D792A
Films	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D882A
MD : Break	34.0	MPa	
TD : Break	40.0	MPa	
Tensile Elongation ²			ASTM D882A
MD : Break	370	%	
TD : Break	410	%	
Elmendorf Tear Strength			ASTM D1922
MD	7.0	g	
TD	7.3	g	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	75.0	°C	ASTM D1525 ³

NOTE	
1.	500 mm/min
2.	500 mm/min
3.	Rate B (120°C/h), Loading 1 (10 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

