

SABIC® PPcompound 3240EH

Polypropylene Homopolymer

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® PPcompound 3240EH is a 40% talc-filled polypropylene homopolymer with good flow, high heat stabilized at low volatiles.

SABIC® PPcompound 3240EH is a designated automotive grade.

General Information			
Filler / Reinforcement	Talc,40% Filler by Weight		
Additive	Heat Stabilizer		
Features	Good Flow		
	Heat Stabilized		
	Homopolymer		
	Low VOC		
Uses	Automotive Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.25	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Molding Shrinkage (24 hr)	0.90	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, Injection Molded)	73		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/5/50
Yield, 3.20 mm, Injection Molded	30.0	MPa	
Break, 3.20 mm, Injection Molded	24.0	MPa	
Tensile Strain (Break, 3.20 mm, Injection Molded)	5.0	%	ISO 527-2/5/50
Flexural Modulus ¹ (Injection Molded)	3600	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C, Injection Molded)	2.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (-40°C, Injection Molded)	5.0	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength			ISO 180/4A
-20°C, Injection Molded	1.5	kJ/m ²	
0°C, Injection Molded	1.6	kJ/m ²	
23°C, Injection Molded	2.8	kJ/m ²	

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	130	°C	ISO 75-2/B
Vicat Softening Temperature	150	°C	ISO 306/A
NOTE			
1.	Method I (3 point load)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

