

ALCOM® PA66 910/1.1 CF15 GF20

Polyamide 66
ALBIS PLASTIC GmbH

Message:

ALCOM®PA66 910/1.1 CF15 GF20 is a polyamide 66 (nylon 66) product, which contains 20% glass fiber reinforced materials and 15% carbon fiber reinforced materials. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. ALCOM®The application fields of PA66 910/1.1 CF15 GF20 include engineering/industrial accessories and automobile industry.

Features include:

- Comply with REACH standard
- ROHS certification
- Conductivity
- Wear-resistant
- heat stabilizer

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
	Carbon fiber reinforced material, 15% filler by weight		
Additive	heat stabilizer		
Features	Conductivity		
	Good wear resistance		
	Thermal Stability		
Uses	Machine/mechanical parts		
	Application in Automobile Field		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	17500	MPa	ISO 527-2
Tensile Stress (Break)	220	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	15500	MPa	ISO 178
Flexural Stress	315	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	60	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	260	°C	ISO 75-2/A

Vicat Softening Temperature	255	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+2	ohms	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	< 80	°C	
Drying Time - Desiccant Dryer	2.0 - 12	hr	
Processing (Melt) Temp	280 - 300	°C	
Mold Temperature	80 - 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

