

# TRILAC® ABS-MP1000

Acrylonitrile Butadiene Styrene  
Polymer Technology and Services, LLC

Message:

TRILAC® ABS-MP1000 is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: flame rated.

General Information			
Features	Platable		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	23	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	103		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	44.8	MPa	ASTM D638
Tensile Elongation (Break)	25	%	ASTM D638
Flexural Modulus	2250	MPa	ASTM D790
Flexural Strength (Yield)	73.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.17 mm)	290	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	89.0	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.59 mm	HB		
3.17 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	87.8 to 93.3	°C	
Drying Time	2.0 to 24	hr	
Rear Temperature	193	°C	
Middle Temperature	216	°C	
Front Temperature	232	°C	
Processing (Melt) Temp	218 to 260	°C	
Mold Temperature	48.9 to 65.6	°C	
Injection Pressure	68.9 to 82.7	MPa	
Injection Rate	Slow-Moderate		

Back Pressure	0.689	MPa
Screw Speed	50 to 60	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

