

ALTECH® PA6 A 2030/319 GF30 IM

Polyamide 6
ALBIS PLASTIC GmbH

Message:

ALTECH® PA6 A 2030/319 GF30 IM is a Polyamide 6 (Nylon 6) product filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America.
Typical application: Housings.
Characteristics include:
REACH Compliant
RoHS Compliant
Good Mold Release
Good Toughness
Heat Stabilizer

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
	Impact Modifier		
Features	Good Mold Release		
	Heat Stabilized		
	Impact Modified		
	Ultra High Toughness		
Uses	Housings		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7500	MPa	ISO 527-2
Tensile Stress	120	MPa	ISO 527-2
Tensile Strain (Break)	3.7	%	ISO 527-2
Flexural Modulus	6850	MPa	ISO 178
Flexural Stress	175	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	20	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	75	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	204	°C	ISO 75-2/A
Vicat Softening Temperature	206	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	80.0	°C	

Drying Time - Desiccant Dryer	2.0 to 12	hr
Suggested Max Moisture	0.15	%
Processing (Melt) Temp	270 to 290	°C
Mold Temperature	80.0 to 100	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

