

Lutene® H ME9180

High Density Polyethylene

LG Chem Ltd.

Message:

LUTENE-H ME9180 is mainly intended for injection molding of complicated parts. It has high productivity and good appearance.

Main Applications:

Complicated parts, light-weight household.

General Information			
Features	Narrow Molecular Weight Distribution		
Uses	Engineering Parts		
	Household Goods		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.958	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	18	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	64		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	28.4	MPa	ASTM D638
Tensile Elongation (Break)	> 1000	%	ASTM D638
Flexural Modulus	981	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (20°C)	39	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	123	°C	ASTM D1525
Melting Temperature	133	°C	DSC

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT