

Polytron® P50N01

Polypropylene Homopolymer

Polyram Ram-On Industries

Message:

A CHEMICALLY COUPLED 50% LONG GLASS FIBER REINFORCED NATURAL POLYPROPYLENE HEAT STABILIZED FOR INJECTION MOULDING APPLICATION.

General Information			
Filler / Reinforcement	Long Glass Fiber,50% Filler by Weight		
Additive	Heat Stabilizer		
Features	Chemically Coupled		
	Heat Stabilized		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage - Flow	0.20 to 0.30	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20 to 0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	12900	MPa	ASTM D638, ISO 527-2
Tensile Strength (Yield)	135	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	1.7	%	ASTM D638, ISO 527-2
Flexural Modulus	11000	MPa	ASTM D790, ISO 178
Flexural Strength	210	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	25	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	75	kJ/m ²	ISO 179
Notched Izod Impact			
23°C	250	J/m	ASTM D256
23°C	25	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	159	°C	ASTM D648, ISO 75-2/A
Flammability	Nominal Value	Test Method	
Flame Rating (3.00 mm)	HB	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

