

# PONYL 4003EPG25

Polyamide 66

POLYROCKS CHEMICAL CO., LTD

Message:

PONYL 4003EPG25 is a Polyamide 66 (Nylon 66) product filled with 25% glass fiber. It is available in Asia Pacific. Typical application: Electrical/Electronic Applications.  
Characteristics include:  
Flame Rated  
Eco-Friendly/Green  
Flame Retardant  
Good Dimensional Stability  
Halogen Free

General Information			
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Features	Environmentally Sound		
	Flame Retardant		
	Good Dimensional Stability		
	Halogen Free		
	High Heat Resistance		
	Low Density		
Uses	Electrical Parts		
	Electrical/Electronic Applications		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (275°C/0.325 kg)	6.5	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	135	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	8500	MPa	ASTM D790
Flexural Strength	200	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	75	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	245	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94

1.50 mm	V-0	
3.00 mm	V-0	
Injection	Nominal Value	Unit
Drying Temperature	100	°C
Drying Time	2.0 to 3.0	hr
Processing (Melt) Temp	245 to 270	°C
Mold Temperature	80.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

