Lucene[™] LC565

Thermoplastic Polyolefin Elastomer

LG Chem Ltd.

Message:

LC565 is an ethylene-1-butene copolymer produced using LG Chem's metallocene polymerization catalyst and solution process technology. This resin is an excellent impact modifier for plastics and offers unique performance capabilities for compounded products. Application General purpose thermoplastic elastomers, Polymer modification Soft and hard TPO compounds Feature Improved impact strength in polypropylene Excellent filler acceptance Available as pellet form Outstanding toughness with flexible performance Reduction of product weight

General Information			
Features	Copolymer		
	Good Flexibility		
	Good Impact Resistance		
	Good Toughness		
Uses	Compounding		
	Plastics Modification		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.865	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	5.0	g/10 min	ASTM D1238
Mooney Viscosity (ML 1+4, 121°C)	8	MU	ASTM D1646
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	54		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	1.80	MPa	ASTM D638
Tensile Elongation ² (Break)	550	%	ASTM D638
Flexural Modulus - 1% Secant	8.00	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ³	20.0	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-54.0	°C	Internal Method
Melting Temperature (DSC)	36.0	°C	Internal Method
NOTE			
1.	510 mm/min		

2.	510 mm/min
3.	Die C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

