

New-prene™ 6175B

Polypropylene + EPDM Rubber
Total Polymer Vision (Suzhou) Co., LTD

Message:

A soft, black color EPDM/PP thermoplastic vulcanizate. This material combines good physical properties and chemical resistance for use in extrusion applications. It is EU directive 2002/95/EC (RoHS) compliant. It is polyolefin based and completely recyclable.

General Information			
Features	Good Chemical Resistance		
	Recyclable Material		
	Soft		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.950	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	75		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	8.30	MPa	ASTM D412
Tensile Elongation (Break)	480	%	ASTM D412
Tear Strength	30.0	kN/m	ASTM D624
Compression Set (70°C, 22 hr)	42	%	ASTM D395
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-55.0	°C	ASTM D746
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Cylinder Zone 1 Temp.	165	°C	
Cylinder Zone 2 Temp.	165 to 180	°C	
Cylinder Zone 3 Temp.	170 to 200	°C	
Melt Temperature	170 to 230	°C	
Die Temperature	180 to 200	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

