

Toraycon® 1101G-X53

Polybutylene Terephthalate

Toray Resin Company

Message:

Toraycon® 1101G-X53 is a Polybutylene Terephthalate (PBT) product filled with 15% glass fiber. It is available in Asia Pacific, Europe, or North America. Characteristics include:
Flame Rated
Good Aesthetics

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Features	Pleasing Surface Appearance		
Part Marking Code	>PBT+P-GF15<		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.44	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (23°C)	97.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.7	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m²	ISO 179
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT