

Shuman ABS 720H

Acrylonitrile Butadiene Styrene

Shuman Plastics, Inc.

Message:

ABS 720H BLACK
OFFERS THIS COMBINATION OF PROPERTIES:
GOOD IMPACT STRENGTH, EASY PROCESSABILITY, GOOD CHEMICAL RESISTANCE

General Information	
Features	Impact resistance, good
	Workability, good
	Good chemical resistance
Appearance	Black
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	2.0 - 6.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	102		ASTM D785
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	240 - 290	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	76.1	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	87.8 - 93.3	°C	
Drying Time	2.0 - 24	hr	
Processing (Melt) Temp	204 - 227	°C	

Injection instructions		
Tray Dryer Drying Temperature, No Standard, 1.5 in: 170 to 200°FTray Dryer Drying Time, No Standard, 1.5 in: 4 to 24hrs		
Extrusion	Nominal Value	Unit
Drying Temperature	87.8 - 93.3	°C
Drying Time	2.0 - 24	hr
Melt Temperature	177 - 216	°C
Extrusion instructions		
Tray Dryer Drying Temperature, No Standard, 1.5 in: 170 to 200°FTray Dryer Drying Time, No Standard, 1.5 in: 4 to 24hrs		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

