

# Braskem PE SHD7255LS-L

High Density Polyethylene

Braskem

Message:

Description:  
SHD7255LS-L is a high-density polyethylene, developed for the injection molding with good tenacity and impact properties combined with a good stiffness. It presents a ratio between melt flow and density that provides excellent mechanical properties. This resin has additives against the action of ultraviolet radiation.  
The minimum biobased content of this grade is 94%, determined according to ASTM D6866.

Application:  
Boxes for frozen food and horticultural products;  
Industrial containers and boxes for general use.

General Information			
Features	Rigid, good		
	High density		
	Updatable resources		
	Compliance of Food Exposure		
Uses	Food service sector		
	General		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.954	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.5	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 2.00 mm, 100% Igepal, F50)	< 5.00	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, Compression Molded)	63		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Compression Molded)	27.0	MPa	ASTM D638
Flexural Modulus - 1% Secant (Compression Molded)	1270	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Compression Molded)	45	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, Compression Molded)	74.0	°C	ASTM D648
Vicat Softening Temperature	127	°C	ASTM D1525 <sup>1</sup>
Additional Information	Nominal Value	Unit	Test Method

Biobased Content	> 94	%	ASTM D6866
NOTE			

1.	压力1 (10N)
----	-----------

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT