# PolyBlend<sup>™</sup> 1100-55A

### Thermoplastic Polyurethane Elastomer Alloy

#### AdvanSource Biomaterials Corp.

#### Message:

. . .

PolyBlend is a family of exceptionally soft, aromatic polyurethane elastomeric alloys, which can be used as a substitute for natural rubber or latex in many applications.

These polymers encompass unique characteristics such as low flexural modulus, moderate tensile strength, and high elongation, in addition to allowing for a high draw-down ratio due to its superior melt strength and chemical integrity.

PolyBlend can be processed on conventional extrusion or injection molding equipment and is available in hardnesses ranging from 45 Shore A to 80 Shore A.

AdvanSource Biomaterials synthesizes and manufactures medical grade materials offering the ability to tailor physical and mechanical characteristics to support and enhance your end product design.

These mechanical characteristic's, critical to the design and development of medical devices, can incorporate a wide range of physical and chemical properties while maintaining core characteristics such as biodurability and biocompatibility. In most materials, specialized characteristics such as the addition of colorant agents or antimicrobial properties (where applicable) can be added to the polymer to provide a homogenous material and limit secondary processing steps.

In addition, radiopaque agents may also be incorporated into the formula to provide additional product enhancements and may contain up to 40%, by weight, of a radiopaque agent thus allowing varied-scale visibility options.

With an expanding range of secondary operations including custom solution development, prototype coating capabilities, and project management services, ASB's expert team of chemists, scientists, engineers and industry professionals assist in every stage of customers' projects, from concept initiation through full-scale manufacture.

General Information					
Features	Aromatic				
	Biocompatible				
	Good Drawdown				
	Good Flexibility				
	Good Melt Strength				
	High Elongation				
	Medium Strength				
	No Animal Derived Components				
	Soft				
Agency Ratings	ISO 10993 Part 5				
Forms	Pellets				
Processing Method	Extrusion				
	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Melt Mass-Flow Rate (MFR) (190°C/2.16					
kg)	2.0 to 26	g/10 min	ASTM D1238		
Water Absorption (Saturation)	0.067 to 0.28	%	ASTM D570		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A)	55		ASTM D2240		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength			ASTM D638		

Break	4.83 to 6.21	MPa	
50% Strain	0.689 to 1.03	MPa	
100% Strain	1.03 to 1.38	MPa	
200% Strain	1.38 to 1.72	MPa	
300% Strain	1.90 to 2.07	MPa	
Tensile Elongation (Break)	950 to 1100	%	ASTM D638

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

