

Franprene TGA 1165

Thermoplastic Elastomer

Franplast S.r.l.

Message:

This compound is ideal for applications where high toughness and strength properties are required. High elastometric percentages guarantee good recovery, an important requirement for this kind of application.

Application:

Support for Bed Stave

General Information			
Features	Good Toughness		
	High Strength		
Uses	Household Goods		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	30	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	65		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	4.50	MPa	ISO 527-2
Nominal Tensile Strain at Break	650	%	ISO 527-2
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	30	kN/m	ISO 34-1
Thermal	Nominal Value	Unit	
Service Temperature	-30 to 70	°C	
Injection	Nominal Value	Unit	
Drying Time	0.0	hr	
Rear Temperature	165 to 185	°C	
Middle Temperature	170 to 190	°C	
Front Temperature	175 to 195	°C	
Nozzle Temperature	180 to 200	°C	
Mold Temperature	30.0 to 40.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

