# POLIMAXX 2500PC

### Polypropylene Impact Copolymer

#### **IRPC** Public Company Limited

#### Message:

2500PC is a Polypropylene Block Copolymer resin for injection molding process with medium flow characteristic. It is suitable for any parts that need high impact strength, like auto parts, electrical, appliances and furniture. It also meets the F.D.A. requirement in the code of federal regulations in 21 CFR 177.1520 for food contact.

| General Information   |                                    |          |             |
|---|------------------------------------|----------|-------------|
| UL YellowCard   | E132283-222116                     |          |             |
| Features  | Block Copolymer                    |          |             |
|   | Food Contact Acceptable            |          |             |
|   | High Impact Resistance             |          |             |
|   | Medium Flow                        |          |             |
|   |                                    |          |             |
| Uses  | Appliance Components               |          |             |
|   | Automotive Applications            |          |             |
|   | Electrical/Electronic Applications |          |             |
|   | Furniture                          |          |             |
|   |                                    |          |             |
| Agency Ratings  | FDA 21 CFR 177.1520                |          |             |
| RoHS Compliance   | RoHS Compliant                     |          |             |
| Processing Method   | Injection Molding                  |          |             |
| Physical  | Nominal Value                      | Unit     | Test Method |
| Melt Mass-Flow Rate (MFR) (230°C/2.16<br>kg)                | 15                                 | g/10 min | ASTM D1238  |
| Hardness  | Nominal Value                      | Unit     | Test Method |
| Rockwell Hardness (R-Scale)                                 | 87                                 |          | ASTM D785   |
| Mechanical  | Nominal Value                      | Unit     | Test Method |
| Tensile Strength (Yield)                                    | 23.0                               | MPa      | ASTM D638   |
| Tensile Elongation (Yield)                                  | 17                                 | %        | ASTM D638   |
| Flexural Modulus - 1% Secant                                | 1100                               | MPa      | ASTM D790   |
| Impact  | Nominal Value                      | Unit     | Test Method |
| Charpy Notched Impact Strength (23°C)                       | 8.0                                | kJ/m²    | DIN 53453   |
| Thermal   | Nominal Value                      | Unit     | Test Method |
| Deflection Temperature Under Load (0.45<br>MPa, Unannealed) | 90.0                               | °C       | ASTM D648   |
| Injection   | Nominal Value                      | Unit     |             |
| Processing (Melt) Temp                                      | 190 to 240                         | °C       |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

