# Greenflex® ML 20

#### Ethylene Vinyl Acetate Copolymer

Versalis S.p.A.

#### Message:

Greenflex ML 20 is an ethylene vinyl acetate copolymer (EVA) for general purpose injection moulding, when a good ESCR resistance is required. Main Application

Greenflex ML 20 is recommended for the production of flexible items.

Features  Copolymer Food Contact Acceptable General Purpose Good Flexibility High ESCR (Stress Crack Resist.)  Uses  General Purpose Agency Ratings EU Food Contact, Unspecified Rating Forms Pellets Processing Method Injection Molding Physical Nominal Value Unit		Test Method
General Purpose Good Flexibility High ESCR (Stress Crack Resist.)  Uses General Purpose Agency Ratings EU Food Contact, Unspecified Rating Forms Pellets Processing Method Injection Molding		
Uses General Purpose Agency Ratings EU Food Contact, Unspecified Rating Forms Pellets Processing Method Injection Molding		
Uses General Purpose Agency Ratings EU Food Contact, Unspecified Rating Forms Pellets Processing Method Injection Molding		
Uses General Purpose  Agency Ratings EU Food Contact, Unspecified Rating  Forms Pellets  Processing Method Injection Molding		
Agency Ratings EU Food Contact, Unspecified Rating Forms Pellets Processing Method Injection Molding		
Agency Ratings EU Food Contact, Unspecified Rating Forms Pellets Processing Method Injection Molding		
Forms Pellets Processing Method Injection Molding		
Processing Method Injection Molding		
Physical Nominal Value Unit		
	cm³	ISO 1183
Density 0.925 g/cn		
Melt Mass-Flow Rate (MFR) (190°C/2.16		
kg) 2.5 g/10	10 min	ISO 1133
Vinyl Acetate Content 7.0 wt%	%	Internal Method
Hardness Nominal Value Unit	nit	Test Method
Shore Hardness		ISO 868
Shore A, Injection Molded 95		
Shore D, Injection Molded 43		
Mechanical Nominal Value Unit	iit	Test Method
Tensile Stress (Yield, Injection Molded) 7.00 MPa	Pa	ISO 527-2
Flexural Modulus (Injection Molded) 100 MPa	Pa	ISO 178
Thermal Nominal Value Unit	iit	Test Method
Brittleness Temperature < -80.0 °C		ASTM D746
Vicat Softening Temperature 78.0 °C		ISO 306/A
Melting Temperature 101 °C		Internal Method
Injection Nominal Value Unit	nit	
Processing (Melt) Temp 150 to 200 °C		
Mold Temperature 10.0 to 30.0 °C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

