

PLEXIGLAS® Film White 99547

PMMA Film

Evonik Industries AG

Message:

PLEXIGLAS® White 99532 and White 99547 Light Scattering Films are based on impact-modified polymethyl methacrylate and offer an ideal combination of transmission and light diffusion. The key properties compared to other materials suitable for illumination purposes are the pure white color, fewer inclusions, extreme weatherability and UV resistance. In addition, these films with two high-gloss surfaces have good resistance to weak acids and alkalis as well as to non-polar solvents.

Applications

PLEXIGLAS® White 99532 and White 99547 Films are universally applicable wherever light scattering is required. Their high transmission combined with superior diffusion provide bright surfaces even with weak light sources.

General Information			
Additive	Impact modifier		
Features	Impact modification		
	Solvent resistance		
	Good UV resistance		
	alkali resistance		
	Good weather resistance		
	acid resistance		
Uses	Illumination diffuser		
Appearance	White		
Forms	Films		
Hardness	Nominal Value	Test Method	
Pencil Hardness	1H	ASTM D3363	
Half-Value Angle - intensity (250.0 µm)	61.5	°	
Films	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-3
Tensile Stress (Yield)	55.0	MPa	ISO 527-3
Tensile Elongation (Yield)	4.5	%	ISO 527-3
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	99.0	°C	ISO 306
CLTE - Flow	1.1E-4	cm/cm/°C	DIN 53752-A
Specific Heat	1500	J/kg/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	ohms · cm	IEC 60093
Dissipation Factor			IEC 60250
100 Hz	0.040		IEC 60250
1 MHz	0.030		IEC 60250
Optical	Nominal Value	Unit	Test Method

Transmittance (250 μm)	54.5	%	DIN 5036
Additional Information	Nominal Value	Unit	

Throwing Power: 0.627 (thickness: 0.25 mm)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

