

Hostacom EKC 265N 2 D72792

Polypropylene Copolymer

LyondellBasell Industries

Message:

Hostacom EKC 265N/2 D72792 is a 20 % talc filled PP copolymer, with high flowability, high stiffness, high UV resistance and good scratch resistance. The product is also available as a customized color matched, pellet form. This grade is delivered in D72792 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Talc filler, 20% filler by weight		
Features	Rigidity, high		
	Rigid, good		
	Copolymer		
	Good UV resistance		
	Good liquidity		
	High liquidity		
	Scratch resistance		
Uses	Car interior equipment		
Appearance	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.04	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	21.0	MPa	ISO 527-2
Tensile Strain (Break)	30	%	ISO 527-2
Flexural Modulus ¹ (23°C)	2000	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	2.5	kJ/m²	ISO 179/1eA
23°C	12	kJ/m²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	105	°C	ISO 75-2/B
Vicat Softening Temperature	140	°C	ISO 306/A
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

