

POLYten HDPE S801

High Density Polyethylene
Polykemi AB

Message:
Good abrasion resistance Excellent sliding properties

| General Information | | | |
|---|--------------------------|-------------------|-------------|
| Features | Good Abrasion Resistance | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.960 | g/cm ³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 kg) | 8.0 | g/10 min | ISO 1133 |
| Mechanical | Nominal Value | Unit | Test Method |
| Flexural Modulus (23°C) | 950 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength (23°C) | 9.0 | kJ/m ² | ISO 179 |
| Charpy Unnotched Impact Strength (23°C) | No Break | | ISO 179 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT