

Rilsan® BZM 30 O TL

Polyamide 11

Arkema

Message:

Rilsan ® BZM 30 O TL is a fibreglass reinforced polyamide 11 produced from a renewable source. This natural grade is designed for injection.

MAIN APPLICATIONS

Quick connectors.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Renewable Resource Content		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.25	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (235°C/5.0 kg)	9.00	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore D	77		
Shore D, 15 sec	74		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7300	MPa	ISO 527-2
Tensile Stress (Break)	137	MPa	ISO 527-2
Tensile Strain (Break)	6.0	%	ISO 527-2
Flexural Modulus	5600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	17	kJ/m ²	
23°C	24	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	96	kJ/m ²	
23°C	89	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	189	°C	ISO 11357-3
Additional Information	Nominal Value	Unit	Test Method
ISO Shortname	PA11, MHLR, 18-070, GF 30		ISO 1874
Renewable Carbon Conent	> 97	%	ASTM D6866
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	4.0 to 6.0	hr	

Processing (Melt) Temp	250 to 290	°C
Mold Temperature	40.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

