

StarFlex P 7335-1000

Thermoplastic Elastomer

STAR Thermoplastic Alloys & Rubbers, Inc.

Message:

StarFlex P 7335-1000 is an easy processing TPE designed for injection molding.

Features

- Soft Touch
- Rubbery Feel
- Excellent Colorability
- Good Weatherability

General Information			
Features	Good Colorability Good Processability Good Weather Resistance Soft		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	35		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain, 23°C)	0.421	MPa	ASTM D412
Tensile Strength (Yield, 23°C)	3.17	MPa	ASTM D412
Tensile Elongation (Break, 23°C)	990	%	ASTM D412
Tear Strength	10.3	kN/m	ASTM D624
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (210°C, 11000 sec ⁻¹)	7.20	Pa·s	ASTM D3835

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT