

Bergamid™ A65 GK15 natur SO

Polyamide 66

PolyOne Corporation

Message:

Bergamid™ A65 GK15 natur SO is a Polyamide 66 (Nylon 66) product filled with 15% glass bead. It is available in Europe. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Bead, 15% Filler by Weight		
Features	General Purpose		
	Good Flow		
Forms	Granules		
Physical	Nominal Value	Unit	Test Method
Density ¹ (23°C)	1.23	g/cm ³	DIN 53479
Molding Shrinkage ² (23°C, 4.00 mm)	1.4 to 1.9	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ³ (23°C, 4.00 mm, Injection Molded)	4100	MPa	ISO 527-2/1
Tensile Stress ⁴ (Break, 23°C, 4.00 mm, Injection Molded)	60.0	MPa	ISO 527-2/5
Tensile Strain ⁵ (Break, 23°C, 4.00 mm, Injection Molded)	1.5	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			
-30°C, Injection Molded	1.4	kJ/m ²	ISO 179
23°C ⁶	2.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			
-30°C, Injection Molded	15	kJ/m ²	ISO 179
23°C, Injection Molded ⁷	15	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	224	°C	ISO 75-2/B
1.8 MPa, Unannealed	75.5	°C	ISO 75-2/A
Maximum Use Temperature			
long term (GTP 50% tensile)	85	°C	IEC 216
short time	180	°C	IEC 60216
Melting Temperature (DSC)	261	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity			IEC 93
-- ⁸	1.0E+10	ohms	

-- 9	1.0E+13	ohms	
Volume Resistivity			IEC 93
-- 10	1.0E+12	ohms·cm	
-- 11	1.0E+15	ohms·cm	
Dissipation Factor ¹² (1 MHz)	1.0E-4		IEC 60250
Comparative Tracking Index ¹³ (Solution A)	500	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
NOTE			
1.	±0.03		
2.	Bergmann method		
3.	dry		
4.	dry		
5.	dry		
6.	dry		
7.	dry		
8.	air humidity		
9.	dry		
10.	air humidity		
11.	dry		
12.	air humidity		
13.	dry		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

