Generic Nylon 6 Elast

Polyamide 6 Elastomer

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic Nylon 6 Elast This information is provided for comparative purposes only.

General Information			
Mechanical	Nominal Value	Unit	Test Method
Tensile Elongation (Break, 23°C)	14 to 200	%	ASTM D638
Flexural Modulus (23°C)	385 to 817	MPa	ASTM D790
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (23°C)	13 to 18	kV/mm	ASTM D149
Dielectric Constant (23°C)	4.00 to 15.2		ASTM D150

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

