

# TECHLEN H7348

Polypropylene  
DAEHA Co., LTD

Message:

TECHLEN H7348 is a Polypropylene material filled with glass fiber. It is available in Asia Pacific. Primary attribute of TECHLEN H7348: High Stiffness.  
Typical application of TECHLEN H7348: Automotive

General Information			
Filler / Reinforcement	Glass Fiber		
Features	High Stiffness		
Uses	Automotive Applications		
	Automotive Under the Hood		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)	10	g/10 min	ASTM D1238

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	94		ASTM D785

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	32.4	MPa	ASTM D638
Flexural Modulus	3240	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C)	59	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	110	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT