

VESTAMID® HTplus M3035

Polyphthalamide

Evonik Industries AG

Message:

VESTAMID HTplus M3035 is a PA10T-based, natural colored, glass-fiber reinforced (50%), heat-stabilized copolyamide. PA10T is a poly-condensation product of 1,10-decamethylene diamine (10) and terephthalic acid (T). As 1,10-decamethylene diamine is derived from castor oil plants, VESTAMID HTplus M3035 is partially natural resourced and thus bio-based.

Compared to PA6T-based resins VESTAMID HTplus M3035 has a broader processing window as well as a reduced tendency to absorb water. Therefore the material exhibits less variation in mechanical properties and dimensional changes with humidity.

This resin is especially suited for manufacturing parts subjected to high temperature.

General Information			
Filler / Reinforcement	Glass Fiber,50% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
	High Heat Resistance		
Uses	High Temperature Applications		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.58	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	15500	MPa	ISO 527-2/1
Tensile Stress (Break)	215	MPa	ISO 527-2
Tensile Strain (Break)	2.2	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-40°C, Complete Break	10	kJ/m ²	
23°C, Complete Break	11	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-40°C, Complete Break	71	kJ/m ²	
23°C, Complete Break	83	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	290	°C	ISO 75-2/B
1.8 MPa, Unannealed	277	°C	ISO 75-2/A
Melting Temperature ¹	285	°C	ISO 11357
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	> 4.0	hr	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

