

ColorFast® FRPE200

Low Density Polyethylene

LTL Color Compounders, Inc.

Message:

Flame Retardant LDPE, non-halogenated

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogen Free		
UL File Number	E178307		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.50 to 0.80	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	89		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	6.89	MPa	
Break	8.96	MPa	
Tensile Elongation ²			ASTM D638
Yield	20	%	
Break	250	%	
Flexural Modulus ³	172	MPa	ASTM D790
Flexural Strength ⁴	6.55	MPa	ASTM D790
Flammability	Nominal Value		Test Method
Flame Rating (2.20 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	48.9	°C	
Drying Time	2.0 to 4.0	hr	
Drying Time, Maximum	6.0	hr	
Suggested Shot Size	40 to 60	%	
Rear Temperature	177 to 199	°C	
Middle Temperature	182 to 204	°C	
Front Temperature	188 to 210	°C	
Nozzle Temperature	193 to 221	°C	
Processing (Melt) Temp	193 to 221	°C	

Mold Temperature	10.0 to 37.8	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm

NOTE

1.	51 mm/min
2.	51 mm/min
3.	51 mm/min
4.	51 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

