# ALCOM® PA66 910/1 GF30 MO2

### Polyamide 66

#### ALBIS PLASTIC GmbH

#### Message:

ALCOM® PA66 910/1 GF30 MO2 is a Polyamide 66 (Nylon 66) product filled with 30% glass fiber. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Applications of ALCOM® PA66 910/1 GF30 MO2 include engineering/industrial parts and automotive. Characteristics include: REACH Compliant Reat Stabilizer Lubricated Wear Resistant

General Information					
Filler / Reinforcement	Glass Fiber,30% Filler by Weight				
Additive	Heat Stabilizer				
	Molybdenum Disulfide Lubricant				
Features	Good Wear Resistance				
	Heat Stabilized				
Uses	Automotive Applications				
	Bearings				
	Gears				
	Machine/Mechanical Parts				
	Wheels				
Agency Ratings	EC 1907/2006 (REACH)				
RoHS Compliance	RoHS Compliant				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Density	1.39	g/cm³	ISO 1183		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Modulus	10000	MPa	ISO 527-2		
Tensile Strain (Break)	3.0	%	ISO 527-2		
Flexural Modulus	9000	MPa	ISO 178		
Flexural Stress	240	MPa	ISO 178		
Impact	Nominal Value	Unit	Test Method		
Charpy Notched Impact Strength	9.0	kJ/m²	ISO 179/1eA		
Charpy Unnotched Impact Strength	55	kJ/m²	ISO 179/1eU		
Thermal	Nominal Value	Unit	Test Method		
Heat Deflection Temperature (1.8 MPa, Unannealed)	250	°C	ISO 75-2/A		

Vicat Softening Temperature	210	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 12	hr	
Processing (Melt) Temp	280 to 300	°C	
Mold Temperature	80.0 to 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

