

POLYMAN® (ABS) LP 299/2 GL A

Acrylonitrile Butadiene Styrene

A. Schulman Europe

Message:

Medium impact ABS grade, antistatic

General Information			
Additive	Antistatic		
Features	Antistatic		
	Medium Impact Resistance		
Processing Method	Injection Molding		
Part Marking Code (ISO 11469)	>ABS<		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	21.0	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	104	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	43.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	2.4	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	11	kJ/m ²	
23°C	21	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	87.0	°C	ISO 75-2/Bf
1.8 MPa, Unannealed	74.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	105	°C	ISO 306/A50
--	96.0	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
1.50 mm	HB		

3.00 mm	HB		
Glow Wire Flammability Index			IEC 60695-2-12
1.50 mm	650	°C	
3.00 mm	650	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
1.50 mm	675	°C	
3.00 mm	675	°C	
Flammability	36	mm/min	FMVSS 302

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

