Karina IVORY PVC COMPOUND BTR-85/200-D-IS-BS

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

OIL RESISTANT PVC COMPOUND RECOMMENDED FOR FLEXIBLE CABLES JACKETING. PU AND NBR ADDITIVATED.

General Information			
Features	Oil Resistant		
Uses	Cable Jacketing		
	Wire & Cable Applications		
Appearance	lvory		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.23 to 1.29	g/cm³	ASTM D792
Color	ОК		ME 12
Color a	-2.21 to 0.790		ME 12
Color b	2.09 to 5.09		ME 12
Color L	79.3 to 82.3		ME 12
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	88 to 92		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 15.7	MPa	ASTM D638
Tensile Elongation (Yield)	> 250	%	ASTM D638
NOTE			
1.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com No. 215, Lianhe North Road, Fengxian District, Shanghai, China

