Resinoid 1322

Phenolic

Resinoid Engineering Corporation

Message:

Resinoid 1322 is a Phenolic product filled with glass fiber. It can be processed by compression molding, injection molding, or resin transfer molding and is available in North America. Applications of Resinoid 1322 include automotive and electrical/electronic applications. Characteristics include: Flame Rated Good Dimensional Stability Heat Resistant Impact Resistant

General Information					
UL YellowCard	E61847-247051				
Filler / Reinforcement	Glass Fiber				
Features	Good Dimensional Stability				
	Good Impact Resistance				
	Good Thermal Stability				
Uses	Automotive Exterior Parts				
	Electrical Parts				
Appearance	Black				
Forms	Pellets				
Processing Method	Compression Molding				
	Injection Molding				
	Resin Transfer Molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.99	g/cm ³	ASTM D792		
Bulk Factor	2.0		ASTM D1895		
Molding Shrinkage - Flow	0.20	%	ASTM D955		
Water Absorption (24 hr)	0.10	%	ASTM D570		
Hardness	Nominal Value	Unit	Test Method		
Rockwell Hardness			ASTM D785		
E-Scale	90				
M-Scale	110				
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield)	64.1	MPa	ASTM D638		
Flexural Modulus	15200	MPa	ASTM D790		
Flexural Strength (Yield)	88.3	MPa	ASTM D790		
Compressive Strength	176	MPa	ASTM D695		

land and		11.2	To al Marilla al
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8			
MPa, Unannealed)	288	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	0.4		
Dielectric Strength	9.4	kV/mm	ASTM D149
Arc Resistance	9.4 190	sec	ASTM D149 ASTM D495
		•	
Arc Resistance	190	sec	ASTM D495
Arc Resistance Flammability	190 Nominal Value	sec	ASTM D495 Test Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

