

Globalene® ST868M

Polypropylene Random Copolymer
Lee Chang Yung Chemical Industry Corp.

Message:

Globalene® ST868M is a Polypropylene Random Copolymer (PP Random Copolymer) material. It is available in Asia Pacific or North America for injection molding or injection stretch blow molding.

Important attributes of Globalene® ST868M are:

- Clarity
- Copolymer
- Impact Resistant

Typical applications include:

- Appliances
- Bottles
- Containers

General Information	
UL YellowCard	E85783-271906
Features	High Clarity
	Low Temperature Impact Resistance
	Random Copolymer
Uses	Appliances
	Bottles
	Containers
UL File Number	E85783
Forms	Pellets
Processing Method	Injection Molding
	Injection Stretch Blow Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.896	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.3	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	84		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	28.4	MPa	ASTM D638
Tensile Elongation (Yield)	12	%	ASTM D638
Flexural Modulus	1030	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	37	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature	86	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

