

LNP™ LUBRILOY™ R2000A compound

Polyamide 66
SABIC Innovative Plastics

Message:

LNP LUBRILOY* R2000A is a compound based on Nylon 66 resin containing Proprietary Lubricant. Added features of this material include: Internally Lubricated.

Also known as: LNP* LUBRILOY* Compound RL

Product reorder name: R2000A

General Information			
UL YellowCard	E45329-101283864		
Additive	Lubricant		
Features	Lubrication		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.02	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	2.6	%	ASTM D955
Transverse flow: 24 hours	2.6	%	ASTM D955
Vertical flow direction: 24 hours	2.6	%	ISO 294-4
Flow direction: 24 hours	2.6	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.30	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.43	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2000	MPa	ASTM D638
--	2100	MPa	ISO 527-2/1
Tensile Strength			
Yield	47.8	MPa	ASTM D638
Yield	43.8	MPa	ISO 527-2
Fracture	43.4	MPa	ASTM D638
Fracture	43.5	MPa	ISO 527-2
Tensile Elongation			
Yield	6.0	%	ASTM D638
Yield	8.8	%	ISO 527-2
Fracture	39	%	ASTM D638
Fracture	30	%	ISO 527-2
Flexural Modulus			
--	1930	MPa	ASTM D790

--	2200	MPa	ISO 178
Flexural Strength			
--	67.8	MPa	ASTM D790
--	69.9	MPa	ISO 178
Coefficient of Friction			
With self-dynamics	0.32		ASTM D3702 Modified
With Self-Static	0.27		ASTM D3702 Modified
Wear Factor - Washer	12.0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	75	J/m	ASTM D256
23°C ²	6.2	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	No Break		ASTM D4812
23°C ³	140	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	6.40	J	ASTM D3763
--	1.70	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	66.1	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	62.8	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁴	67.0	°C	ISO 75-2/Af
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm, Testing by SABIC)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 - 0.25	%	
Rear Temperature	266 - 277	°C	
Middle Temperature	282 - 293	°C	
Front Temperature	293 - 304	°C	
Processing (Melt) Temp	271 - 282	°C	
Mold Temperature	82.2 - 93.3	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

