# KRATON® D1119 P

### Styrene Isoprene Styrene Block Copolymer

#### Kraton Polymers LLC

#### Message:

Kraton D1119 P is a clear, linear triblock copolymer based on styrene and isoprene with a polystyrene content of 22%. It is supplied from North America in the physical form identified below.

Kraton D1119 PT - supplied as a dusted dense pellet

Kraton D1119 PSM - supplied as a powder dusted with silica

Kraton D1119 P is used as an ingredient in formulating adhesives, sealants and coatings. It may also find use as a modifier of bitumen or thermoplastics and in compound formulations.

General Information	
Additive	Antioxidant
Features	Antioxidant
	Copolymer
Uses	Adhesives
	Asphalt Modification
	Coating Applications
	Compounding
	Plastics Modification
	Sealants
Appearance	Clear/Transparent
Forms	Pellets
	Powder
Processing Method	Coating
	Compression Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.930	g/cm³	ASTM D4025
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	25	g/10 min	
Antioxidant Additive	0.080 to 0.30	%	Internal Method
Ash Content			
PSM	2.5 to 5.0	%	ISO 247
T, Talc	0.30 to 0.40	%	Internal Method
Polystyrene Content	21 to 24	%	Internal Method
Total Extractables	< 1.0	%	Internal Method
Volatile Matter	< 0.50	%	Internal Method
Diblock Content	66.0		
Styrene/Rubber ratio	22/78		

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec, Compression Molded)	30		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	1.10	MPa	ASTM D412
Tensile Strength (Yield)	2.41	MPa	ASTM D412
Tensile Elongation (Break)	1000	%	ASTM D412

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

