Mowital® B 60 H

Polyvinyl Butyral

Kuraray Co., Ltd.

Message:

Characteristics

Polyvinyl butyral (PVB) grades with different molecular weights, and varying degrees of acetalization.

Recommended Uses

Binder for coatings (adhesion promotion/corrosion protection primers, shop primers, wash primers, stoving enamels, varnishes and lacquers for different substrates). Binder for printing inks. Co-binder for powder coatings. Temporary binder for ceramics. Binder for textile printing and non-woven. Wetting agent for grindings, esp. of organic pigments. Adhesives, pressure-sensitive adhesives and hotmelts.

| General Information | | | |
|--|---|-------|-------------|
| Features | Crosslinkable | | |
| | Food Contact Acceptable | | |
| | Heat Sealable | | |
| | | | |
| Uses | Adhesives | | |
| | Binder | | |
| | | | |
| Agency Ratings | EU 2002/72/EC | | |
| | EU 2004/19/EC | | |
| | FDA 21 CFR 175.105 | | |
| | FDA 21 CFR 175.300 | | |
| | FDA 21 CFR 176.170 | | |
| | | | |
| Appearance | White | | |
| Forms | Powder | | |
| Physical | Nominal Value | Unit | Test Method |
| Apparent Density | 0.25 | g/cm³ | DIN EN 543 |
| Water Absorption (20°C, 24 hr, 0.100 mm) | 4.0 to 6.0 | % | |
| Solution Viscosity ¹ | 160 to 260 | mPa·s | DIN 53015 |
| Thermal | Nominal Value | Unit | Test Method |
| Glass Transition Temperature | 70.0 | °C | ISO 11357-2 |
| Additional Information | Nominal Value | Unit | Test Method |
| Non-Volatile Content | > 97.5 | wt% | DIN 53216 |
| Polyvinyl Acetate Content ² | 1.0 to 4.0 | wt% | |
| Polyvinyl Alcohol Content ³ | 18.0 to 21.0 | wt% | |
| NOTE | | | |
| | According to Hoeppler, 10% | | |
| 1. | solution in Ethanol containing 5% water at 20°C | | |
| 1. | | | |
| 2. | Acetyl groups in terms of polyvinyl acetate | | |

3.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

