

Badamid® LA70 GF30 H

Polyamide 66

Bada AG

Message:

Badamid® LA70 GF30 H is a Polyamide 66 (Nylon 66) material filled with 30% glass fiber. It is available in Europe. Primary attribute of Badamid® LA70 GF30 H: Flame Rated.

General Information			
UL YellowCard	E189230-227352	E189230-102029063	
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Density	1.35	g/cm³	ISO 1183
Water Absorption			ISO 62
Saturation, 23°C	6.0	%	
Equilibrium, 23°C, 50% RH	2.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	9500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	170	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.3	%	ISO 527-2/5
Flexural Stress (23°C)	280	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	12	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	80	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	250	°C	ISO 75-2/B
1.8 MPa, Unannealed	250	°C	ISO 75-2/A
Melting Temperature (DSC) ¹	262	°C	ISO 3146
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.60 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	285 to 305	°C	
Mold Temperature	80.0 to 90.0	°C	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

