

Hostaform® MT8U01

Acetal (POM) Copolymer

Celanese Corporation

Message:

Hostaform® acetal copolymer grade MT8U01 is a special grade developed for medical industry applications containing low residual monomers and no animal products. Hostaform® MT8U01 is an injection molding grade with a molecular weight for excellent moldability and optimum properties in demanding applications.

General Information			
Features	Good formability		
	Good liquidity		
Uses	Medical/nursing supplies		
RoHS Compliance	Contact manufacturer		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	8.00	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction	1.8	%	ISO 294-4
Flow direction	2.0	%	ISO 294-4
Water Absorption (Saturation, 23°C)	0.65	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2850	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	64.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	9.0	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	30	%	ISO 527-2/1A/50
Tensile Creep Modulus			ISO 899-1
1 hr	2500	MPa	ISO 899-1
1000 hr	1300	MPa	ISO 899-1
Flexural Modulus (23°C)	2700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	6.0	kJ/m ²	ISO 179/1eA
23°C	6.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	160	kJ/m ²	ISO 179/1eU
23°C	180	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	104	°C	ISO 75-2/A

Melting Temperature ¹	166	°C	ISO 11357-3
CLTE - Flow	1.1E-4	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.15	%	
Hopper Temperature	20.0 - 30.0	°C	
Rear Temperature	170 - 180	°C	
Middle Temperature	180 - 190	°C	
Front Temperature	190 - 200	°C	
Nozzle Temperature	190 - 210	°C	
Processing (Melt) Temp	190 - 210	°C	
Mold Temperature	80.0 - 120	°C	
Injection instructions			
Manifold Temperature: 190 to 210°CZone 4 Temperature: 190 to 210°CFeed Temperature: 60 to 80°C			
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT