

Generic PC - Unspecified

Polycarbonate

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic PC - Unspecified
This information is provided for comparative purposes only.

General Information			
Filler / Reinforcement	Filler		
Physical	Nominal Value	Unit	Test Method
Molding Shrinkage (23°C)	0.59 - 0.60	%	ISO 294-4
Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index	850 - 960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Mold Temperature	79.1 - 100	°C	
Injection instructions			

This data represents typical values that have been calculated from all products classified as: Generic PC - UnspecifiedThis information is provided for comparative purposes only.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

