

Ferro PP LPP40BD28WH

Polypropylene Homopolymer

Ferro Corporation

Message:

Ferro PP LPP40BD28WH is a Polypropylene Homopolymer (PP Homopolymer) material filled with 41% calcium carbonate. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding. Primary attribute of Ferro PP LPP40BD28WH: Homopolymer.

General Information			
Filler / Reinforcement	Calcium Carbonate,41% Filler by Weight		
Features	Homopolymer		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	1.3	%	
Across Flow	1.5	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	24.1	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	25	%	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 23°C	2280	MPa	
Tangent : 23°C	2550	MPa	
Flexural Strength (23°C)	41.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	32	J/m	ASTM D256
Unnotched Izod Impact (23°C)	440	J/m	ASTM D4812
Gardner Impact (23°C)	3.95	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	118	°C	
1.8 MPa, Unannealed	68.3	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

