

Thermoset Plastics 300 No.70

Epoxy; Epoxide

Thermoset, Lord Chemical Products

Message:

Thermoset Plastics 300 No.70 is an Epoxy; Epoxide (Epoxy) material. It is available in North America for casting or encapsulating.

Important attributes of Thermoset Plastics 300 No.70 are:

Conductive

Heat Resistant

Impact Resistant

Insulating

Typical application of Thermoset Plastics 300 No.70: Wire & Cable

General Information			
Features	Electrically Insulating		
	Good Impact Resistance		
	Good Thermal Shock Resistance		
	Thermally Conductive		
Uses	Electronic Insulation		
Appearance	Black		
Forms	Pellets		
Processing Method	Casting		
	Encapsulating		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.50	g/cm ³	ASTM D792
Water Absorption (24 hr)	0.21	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	88		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	67.6	MPa	ASTM D638
Tensile Elongation (Yield)	4.4	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	29	J/m	ASTM D256
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	7.0E+15	ohms · cm	ASTM D257
Dielectric Constant (1 MHz)	3.90		ASTM D150
Dissipation Factor (1 MHz)	0.032		ASTM D150
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Hardener	Mix Ratio by Weight: 15		
Resin	Mix Ratio by Weight: 100		

Thermoset Mix Viscosity (25°C)	2000	cP	ASTM D2393
Demold Time (25°C)	1400	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

