

# Matrixx FPP1A10CC

Polypropylene

The Matrixx Group, Inc.

## Message:

Matrixx FPP1A10CC is a polypropylene material, and the filler is 10% glass fiber reinforced material. This product is available in North America and is processed by injection molding.

The main features of the Matrixx FPP1A10CC are:

flame retardant/rated flame

Chemical coupling

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Features	Chemical coupling		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.958	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.30 - 0.60	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	48.3	MPa	ASTM D638
Flexural Modulus - Tangent	2480	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	149	°C	ASTM D648
1.8 MPa, not annealed	129	°C	ASTM D648
RTI	65.6	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2 - 104	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	199 - 243	°C	
Middle Temperature	199 - 243	°C	
Front Temperature	199 - 243	°C	
Processing (Melt) Temp	199 - 243	°C	
Mold Temperature	15.6 - 65.6	°C	
Injection Rate	Moderate		
Back Pressure	< 0.345	MPa	

Screw Speed	20 - 60	rpm
Cushion	6.35 - 12.7	mm
Injection instructions		
Drying not normally required		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

