

# Ravago Compounds HMP-305U (Roto)

Linear Low Density Polyethylene  
Ravago Manufacturing Americas, LLC

Message:

- Key Features:
- 35-mesh powder
  - Utility Grade
  - Good long term outdoor weatherability
  - Balance of toughness and rigidity
  - Good low temperature impact
  - Good environmental stress crack resistance, ESCR
  - Compounded for uniform additive dispersion
  - Natural as well as standard, custom or special effect colors available
  - Stock colors may be available. See Stock color bulletin
  - UL component recognition listing (E141240)
  - Also available in pellet form as HM-305U

General Information			
Features	Good Toughness		
	Good Weather Resistance		
	High ESCR (Stress Crack Resist.)		
	High Rigidity		
	Low Temperature Impact Resistance		
UL File Number	E141240		
Appearance	Colors Available		
	Natural Color		
Forms	Powder		
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.936	g/cm <sup>3</sup>	ASTM D792
Apparent Density <sup>1</sup>	0.34	g/cm <sup>3</sup>	ASTM D1895
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, Rotational Molded)	19.3	MPa	ASTM D638
Flexural Modulus - Tangent (Rotational Molded)	758	MPa	ASTM D790
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.52 mm	HB		
3.05 mm	HB		
Additional Information	Nominal Value	Unit	Test Method

Pourability <sup>2</sup>	30.0	sec	ASTM D1895
NOTE			
1.	35-mesh powder		
2.	35-mesh powder		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

