

Hanwha Total TPE SE65

Thermoplastic Elastomer

HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:

SE65 Thermoplastic Elastomer is a dynamically fully cured thermoplastic elastomer. There is no vulcanization, and this is shipped pre-mixed an ready to process. This can be processed on extrusion,injection and blow molding equipment for faster molding cycle times and lower per-part costs.

General Information			
Features	Fast Molding Cycle		
	Good Chemical Resistance		
	Good Dimensional Stability		
	Good Processability		
	Good Weather Resistance		
	Low Compression Set		
	Oil Resistant		
	Recyclable Material		
Uses	Automotive Exterior Parts		
	Automotive Interior Parts		
	Blow Molding Applications		
	Cable Jacketing		
	Electrical Parts		
	Seals		
	Wire Jacketing		
Forms	Pellets		
Processing Method	Blow Molding		
	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm ³	ASTM D1505
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 5 sec)	65		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	6.08	MPa	ASTM D412
Tensile Elongation (Break)	300	%	ASTM D412
Tear Strength	24.5	kN/m	ASTM D624
Compression Set (25°C, 70 hr)	30	%	ASTM D395
Thermal	Nominal Value	Unit	Test Method

Brittleness Temperature	-60.0	°C	ASTM D746
Injection	Nominal Value	Unit	
Rear Temperature	180 to 190	°C	
Middle Temperature	180 to 190	°C	
Front Temperature	180 to 190	°C	
Processing (Melt) Temp	200	°C	
Mold Temperature	30.0 to 60.0	°C	
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	170 to 180	°C	
Cylinder Zone 2 Temp.	180 to 190	°C	
Cylinder Zone 3 Temp.	180 to 190	°C	
Adapter Temperature	190 to 200	°C	
Die Temperature	200 to 210	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

