

UNISOFT TPE™ ST-43A-CL-1-01

Styrene Ethylene Butylene Styrene Block Copolymer

UNITED SOFT PLASTICS, Inc.

Message:

TPE Compound based on Styrene-Ethylene/Butylene-Styrene Block Copolymer

General Information			
Features	Bondability		
	Good Adhesion		
	Good Processability		
	High Clarity		
	High Elasticity		
	Low Density		
	Low Viscosity		
Uses	Adhesives		
	Bonding		
Agency Ratings	FDA Unspecified Rating		
Appearance	Translucent		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.890	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.0 to 3.5	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	43		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	5.90	MPa	ASTM D412
Tensile Elongation (Break)	700	%	ASTM D412
Injection	Nominal Value	Unit	
Rear Temperature	160 to 180	°C	
Front Temperature	160 to 180	°C	
Nozzle Temperature	200 to 215	°C	
Mold Temperature	30.0 to 65.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

