

BJB Polyurethane TC-892 A/B FR

Polyurethane
BJB Enterprises, Inc.

Message:
TC-892 A/B FR incorporates a non-mercury based catalyst system that produces a tough 80 shore D material with a 20-25 minute work time. This system can be used to hand pour large electronic housing, models of all kinds, and point of purchase items.

General Information			
UL YellowCard	E174527-609644		
Features	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Electrical housing		
Appearance	White		
	Opacity		
Forms	Liquid		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	80		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1810	MPa	ASTM D638
Tensile Strength	44.1	MPa	ASTM D638
Tensile Elongation (Break)	4.6	%	ASTM D638
Flexural Modulus	2270	MPa	ASTM D790
Flexural Strength	78.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	29	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	90.6	°C	ASTM D648
1.8 MPa, not annealed	83.9	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94
Thermoset	Nominal Value	Unit	Test Method
Shelf Life	26	wk	
Thermoset Mix Viscosity (25°C)	975	cP	ASTM D2393
Demold Time (25°C)	300 - 360	min	
Post Cure Time (82°C)	16	hr	

Additional Information

Shrinkage linear, 12" x 0.5" x 0.5": 0.003 in/in Mix ratio by weight: 70/100 Mix ratio by volume: 79/100 Work time, 100 g, 77°F: 20-25 min gel time: 30-35 min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

